



# AEC-NASA TECH BRIEF



AEC-NASA Tech Briefs announce new technology derived from the research and development program of the U.S. AEC or from AEC-NASA interagency efforts. They are issued to encourage commercial application. Tech Briefs are available on a subscription basis from the Clearinghouse for Federal Scientific and Technical Information, Springfield, Virginia 22151. Requests for individual copies or questions relating to the Tech Brief program may be directed to the Technology Utilization Division, NASA, Code UT, Washington, D.C. 20546.

## Low-Temperature Radiation-Resistant Material for Ball-Bearing Retainers

A new material, made of polyimide polymers and S-glass (alumina-silica-magnesia) cloth and developed in the nuclear-rocket program, may replace fiberglass-reinforced polytetrafluoroethylene in ball-bearing retainers for extreme environments. The fluorocarbon material weakens badly at cryogenic temperatures and after nuclear radiation doses exceeding  $10^9$  erg/g. The new material shows satisfactory wear resistance, lubricity, and stability.

The S-glass cloth is wound on a mandrel of preset diameter matched in size with the bearing retainer. The cloth is impregnated with polybenzimidazole (PBI), in powder-slurry form, placed between and over the windings. The laminate is cured in five heat cycles ranging from  $70^\circ$  to  $700^\circ\text{F}$  at pressure between 0 and 100 lb/in<sup>2</sup> (gage). The cured part is machined to final size.

Polybenzimidazole has greater thermal stability than the fluorocarbons because of a greater degree of chain condensation. A major advantage in the use of S-glass is its freedom from elements such as boron that could become involved in nuclear reactions.

The following results were typical of comparative tests of the PBI and fluorocarbon materials: (1) while irradiation increased PBI's strength by 15%, it reduced the latter's by 81%; (2) while the PBI's rate of wear was slightly inferior at from 8500 to 12,200 rpm in liquid hydrogen, it was still acceptable; (3) after irradiation to  $2 \times 10^{10}$  erg/g, a retainer made of PBI was tested successfully for 3 hr at 24,000 rpm.

### Note:

Requests for further information may be directed to:  
Technology Utilization Officer  
AEC-NASA Space Nuclear Propulsion Office  
U.S. Atomic Energy Commission  
Washington, D.C. 20545  
Reference: B70-10576

### Patent status:

No patent action is contemplated by AEC or NASA.  
Source: P. O. Desau and W. F. Emmons of  
Aerojet-General Corp.  
under contract to  
Space Nuclear Propulsion Office  
(NUC-10058)

Category 04